

NATIONAL AERONAUTICS AND SPACE ADMINISTRATION

*Technical Memorandum 33-565*

*Theoretical Determination of Cesiated  
Work Functions*

*R. M. Szejn*

(NASA-CR-128339) THEORETICAL DETERMINATION  
OF CESIATED WORK FUNCTIONS R.M. Szejn (Jet  
Propulsion Lab.) 15 Sep. 1972 19 p CSCL 20L


N72-33712

Unclas  
G3/26 44060

**JET PROPULSION LABORATORY  
CALIFORNIA INSTITUTE OF TECHNOLOGY  
PASADENA, CALIFORNIA**

September 15, 1972

Reproduced by  
**NATIONAL TECHNICAL  
INFORMATION SERVICE**  
U S Department of Commerce  
Springfield VA 22151



1. Report No. 33-565		2. Government Accession No.		3. Recipient's Catalog No.	
4. Title and Subtitle THEORETICAL DETERMINATION OF CESIATED WORK FUNCTIONS				5. Report Date September 15, 1972	
				6. Performing Organization Code	
7. Author(s) R. M. Szejn				8. Performing Organization Report No.	
9. Performing Organization Name and Address JET PROPULSION LABORATORY California Institute of Technology 4800 Oak Grove Drive Pasadena, California 91103				10. Work Unit No.	
				11. Contract or Grant No. NAS 7-100	
12. Sponsoring Agency Name and Address NATIONAL AERONAUTICS AND SPACE ADMINISTRATION Washington, D.C. 20546				13. Type of Report and Period Covered Technical Memorandum	
				14. Sponsoring Agency Code	
15. Supplementary Notes					
16. Abstract  A computer program based on the theoretical work of Gyftopoulos, Steiner, and Levine on bimetallic systems and using a modified version of Wilkins' SIMCON subroutine SURFAS has been written for the UNIVAC 1108. This program, WFGSL, accepts the operating conditions and the physical parameters pertinent to the substrate and adsorbate and outputs the field-free work function, electron current (Richardson equation), ion current (Saha equation), and fractional substrate coverage by the adsorbate. A brief description of the theory is presented together with a program description and listing. An application of the program to a bimetallic system of cesium (adsorbate) and rhenium (substrate) is also described.					
17. Key Words (Selected by Author(s))  Computer Programs Surface Physics Thermionics			18. Distribution Statement  Unclassified -- Unlimited		
19. Security Classif. (of this report) Unclassified		20. Security Classif. (of this page) Unclassified		21. No. of Pages 18	
				22. Price \$3.00	

## HOW TO FILL OUT THE TECHNICAL REPORT STANDARD TITLE PAGE

Make items 1, 4, 5, 9, 12, and 13 agree with the corresponding information on the report cover. Use all capital letters for title (item 4). Leave items 2, 6, and 14 blank. Complete the remaining items as follows:

3. Recipient's Catalog No. Reserved for use by report recipients.
7. Author(s). Include corresponding information from the report cover. In addition, list the affiliation of an author if it differs from that of the performing organization.
8. Performing Organization Report No. Insert if performing organization wishes to assign this number.
10. Work Unit No. Use the agency-wide code (for example, 923-50-10-06-72), which uniquely identifies the work unit under which the work was authorized. Non-NASA performing organizations will leave this blank.
11. Insert the number of the contract or grant under which the report was prepared.
15. Supplementary Notes. Enter information not included elsewhere but useful, such as: Prepared in cooperation with... Translation of (or by)... Presented at conference of... To be published in...
16. Abstract. Include a brief (not to exceed 200 words) factual summary of the most significant information contained in the report. If possible, the abstract of a classified report should be unclassified. If the report contains a significant bibliography or literature survey, mention it here.
17. Key Words. Insert terms or short phrases selected by the author that identify the principal subjects covered in the report, and that are sufficiently specific and precise to be used for cataloging.
18. Distribution Statement. Enter one of the authorized statements used to denote releasability to the public or a limitation on dissemination for reasons other than security of defense information. Authorized statements are "Unclassified-Unlimited," "U. S. Government and Contractors only," "U. S. Government Agencies only," and "NASA and NASA Contractors only."
19. Security Classification (of report). NOTE: Reports carrying a security classification will require additional markings giving security and downgrading information as specified by the Security Requirements Checklist and the DoD Industrial Security Manual (DoD 5220.22-M).
20. Security Classification (of this page). NOTE: Because this page may be used in preparing announcements, bibliographies, and data banks, it should be unclassified if possible. If a classification is required, indicate separately the classification of the title and the abstract by following these items with either "(U)" for unclassified, or "(C)" or "(S)" as applicable for classified items.
21. No. of Pages. Insert the number of pages.
22. Price. Insert the price set by the Clearinghouse for Federal Scientific and Technical Information or the Government Printing Office, if known.

NATIONAL AERONAUTICS AND SPACE ADMINISTRATION


*Technical Memorandum 33-565*

*Theoretical Determination of Cesium  
Work Functions*

*R. M. Szejn*

**JET PROPULSION LABORATORY  
CALIFORNIA INSTITUTE OF TECHNOLOGY  
PASADENA, CALIFORNIA**

September 15, 1972



Prepared Under Contract No. NAS 7-100  
National Aeronautics and Space Administration

PRECEDING PAGE BLANK NOT FILMED

## PREFACE

The work described in this report was performed by the Guidance and Control Division of the Jet Propulsion Laboratory.

Preceding page blank

## CONTENTS

I.	Introduction . . . . .	1
II.	Theory . . . . .	1
III.	Program . . . . .	3
IV.	Results . . . . .	4
V.	Conclusion . . . . .	4
	References . . . . .	5
	Appendix A. Program Listing . . . . .	11
	Appendix B. Program Output . . . . .	16

## TABLE

1.	Input parameters . . . . .	6
----	----------------------------	---

## FIGURES

1.	Bonding interactions . . . . .	7
2.	Maximum ligancy on the 111-plane of tungsten . . . . .	7
3.	SURFAS subroutine flowchart . . . . .	8
4.	Variation in $\phi (T_S/T_R, \phi_0)$ . . . . .	8
5.	Variation in $\phi (T_S/T_R, \sigma_s)$ . . . . .	9
6.	Variation in $\phi (T_S/T_R, \sigma_a)$ . . . . .	9
7.	Variation in $\phi (T_S/T_R, D_1)$ . . . . .	10
8.	Rhenium work function . . . . .	10
B-1.	Work function vs temperature ratio . . . . .	18

## ABSTRACT

A computer program based on the theoretical work of Gyftopoulos, Steiner, and Levine on bimetallic systems and using a modified version of Wilkins' SIMCON subroutine SURFAS has been written for the UNIVAC 1108. This program, WFGSL, accepts the operating conditions and the physical parameters pertinent to the substrate and adsorbate and outputs the field-free work function, electron current (Richardson equation), ion current (Saha equation), and fractional substrate coverage by the adsorbate. A brief description of the theory is presented together with a program description and listing. An application of the program to a bimetallic system of cesium (adsorbate) and rhenium (substrate) is also described.



## I. INTRODUCTION

In thermionic energy conversion, the work function of an emitter in contact with cesium vapor is a controlling parameter determining the rate of electron emission and thus converter efficiency. An understanding of the adsorbate-substrate interaction is essential to the development of more efficient thermionic converters. The theoretical work of Gyftopoulos, Steiner, and Levine (Refs. 1, 2) on the general bimetallic system evaluates the work function of this system as a function of its physical parameters.

This theory has been incorporated in a program using a modified version of Wilkins' SIMCON subroutine SURFAS (Ref. 3). The program serves as a tool in evaluating possible changes in a converter due to changes in the work function of the emitting surface with time. Although cesium is the only adsorbate considered here, the computer program is general in nature and can be used for other bimetallic systems. The program accepts the operating conditions and the physical parameters pertinent to the substrate and adsorbate and outputs the field-free work function, electron current, ion current, and fractional substrate coverage by the adsorbate. The code differs from Wilkins' program in format usage, input parameters, and output information; the printed plus graphical output facilitates the comparison of theoretical and experimental work.

## II. THEORY

The work function of a pure metal can be identified with the neutral electronegativity of valence orbitals in the surface atoms. Using this approach, the work function for a bimetallic surface can be viewed as a perturbation from the bare work function. The perturbation arises from substrate-adsorbate (s-f) and adsorbate-adsorbate (f-f) interactions (Fig. 1). In an s-f bond, there is a charge transfer due to a difference in the

electronegativities of the atoms. This charge transfer results in a dipole double layer whose electrostatic potential is superimposed on the electronegativity of the substrate atoms. The perturbation which results is taken to be proportional to the electronic charge transferred,  $F$ . The f-f bond resulting from charge overlap also produces an electrostatic potential, again affecting the bare substrate electronegativity. This perturbation is assumed proportional to the amount of charge overlap,  $Q$ . Thus, our basic relation (Refs. 1, 2) is

$$\phi = \phi_s + cQ + bF, \quad (1)$$

where  $\phi$  is the perturbed neutral electronegativity,  $\phi_s$  is the bare substrate work function (unperturbed neutral electronegativity), and  $c$  and  $b$  are constants of proportionality. Observe that  $\phi = \phi_s$  at  $\theta = 0$  ( $\theta$  is the fraction of substrate coverage by the adsorbate) since  $Q$  and  $F$  are zero by definition.

It is found experimentally that with a one-monolayer coverage ( $\theta = 1$ ), the work function is approximately equal to the adsorbate work function,  $\phi_f$ :

$$\phi = \phi_f, \quad \theta = 1. \quad (2)$$

Equation (2) is therefore a boundary condition for (1).

The quantities  $cQ$  and  $bF$  may be derived, and result in the following equations:

$$cQ = -(\phi_s - \phi_f)M, \quad (3)$$

where  $M$  is a Morse function defined by

$$M = 2 \exp \left[ +ad_0(1 - \theta^{-1/2}) \right] - \exp \left[ +2ad_0(1 - \theta^{-1/2}) \right], \quad (4)$$

where  $ad_0 = 2.97$ .

For  $bF$  it is found (Ref. 1) that

$$b = \frac{-0.905 (10^{-6}) V_f (R \cos \beta) \sigma_f \theta}{\left(1 + \frac{\alpha}{R^3}\right) \left(1 + 9\alpha \sigma_f^{3/2} \theta^{3/2}\right)} \text{ eV/coulomb}, \quad (5)$$

$$\frac{F}{e} = \frac{(\phi_s - \phi_f)(1 - M)}{D_0 \left(\frac{1 - F^2}{e^2}\right)^{-1/2} + D_1}, \quad (6)$$

where  $V_f$  is the number of bonding orbitals per adatom,  $R$  and  $\beta$  are defined in Fig. 2,  $\sigma_f$  is the adsorbate density,  $D_0$  is the energy of the purely covalent s-f bond, and  $D_1$  is an adjustable parameter, which may be approximated by (Ref. 1)  $D_1 = 1.3 (\phi_s + \phi_f) (-28.75/R)$ , where  $R$  is in Å. Note that (2) is satisfied since  $F(1) = 0$ .

### III. PROGRAM

The program logic determining the cesiated work function  $\phi$  and the fractional coverage  $\theta$  as functions of  $T_S$  and  $T_R$  consists of two nested iteration loops. The inner loop uses Newton's method to solve for  $F$  in (6), assuming an initial value of 0.5 for  $\theta$  and 0.5 for  $F$ . After solving for  $F$ , the arrival rate is set equal to the desorption rate of adsorbate atoms. Since the latter quantity is a function of both  $\phi$  and  $\theta$ , it will not equal the arrival rate for the initial guess of  $\theta$ . Thus  $\theta$  is changed accordingly to bring the arrival and desorption rates into equality. Having adjusted  $\theta$  according to the difference between the arrival and desorption rates, it is now necessary to recalculate  $F$  to determine the new value of  $\phi$ . Figure 3 presents a flowchart of the SURFAS subroutine. Table 1 presents the input parameters. Besides the output listed in the introduction, WFGSL uses the CalComp plotter to generate a graph of  $\phi$  versus  $T_S/T_R$ . A listing of WFGSL is given in Appendix A, along with a sample data deck and the corresponding output (Appendix B).

## IV. RESULTS

The results appearing in Figs. 4-8 are for a rhenium substrate and cesium adsorbate. The physical constants that were used appear in the data deck of Appendix A. The curves in Figs. 4-7 show the dependence of the work function  $\phi$  on the parameters  $\phi_0$ ,  $\sigma_s$ ,  $\sigma_a$ ,  $D_1$  (bare work function, substrate density, adsorbate density, and adjustable parameter, respectively).

In Fig. 4,  $\phi$  is plotted as a function of the ratio between substrate and adsorbate temperature for various values of the bare work functions. As is expected, a change in the bare work function results in a vertical displacement in the curves. Figure 5 shows the effect of varying the substrate density  $\sigma_s$  while keeping the adsorbate density fixed. The effect is seen to be most pronounced for smaller values of  $T_S/T_R$ , where the fractional coverage and thus the substrate-adsorbate interactions are greatest. In Fig. 6, the substrate density is held constant while the adsorbate density is varied. The curves show the strong dependence of  $\phi$  on the adsorbate; with increasing adsorbate density the work function is lowered significantly even at high substrate-adsorbate temperature ratios. Figure 7 shows that cesiated work functions shift by a constant amount over the entire range of temperature ratios as the adjustable parameter  $D_1$  is varied. In Fig. 8 an experimental curve (Ref. 4) is shown together with a theoretical curve generated by WFGSL. The agreement is seen to be excellent.

## V. CONCLUSION

A computer program, WFGSL, based on Gyftopoulos, Steiner, and Levine's work on bimetallic systems and using a modified version of Wilkins' SIMCON subroutine SURFAS has been developed for use on the UNIVAC 1108. The program determines the field-free cesiated work function, electron current, ion current, and fractional substrate coverage by the adsorbate. The indicated relation between  $\phi$ , the calculated work function, and the various physical input parameters is found to be consistent with expectations; agreement between experimental work functions and theoretical work functions is shown to be good.

## REFERENCES

1. Gyftopoulos, Elias P., and Levine, Jules D., "Work Function Variation of Metals Coated by Metallic Films," J. Appl. Phys., 33, 67, 1962.
2. Gyftopoulos, Elias P., and Steiner, Don, "Orbital Electronegativity and Physical Properties of Bimetallic Adsorption Systems," Report on Twenty-Seventh Annual Physical Electronics Conference, Cambridge, Mass., p. 169, Mar. 1967.
3. Wilkins, D. R., SIMCON: A Digital Computer Program for Computing Thermionic Converter Performance Characteristics, AEC R&D Report GESR-2109, General Electric Co., Pleasanton, Calif., Jan. 1970.
4. Shimada, K., and Cassell, P. L., Evaluation of Converters Fueled With Uranium Nitride, Technical Memorandum 33-489, Jet Propulsion Laboratory, Pasadena, Calif., July 30, 1971.

Table 1. Input parameters

Card	Columns	Parameter	Units	Format
1	1-5	Number of independent cases $\geq 1$	—	I5
	6-80	Blank		
Parameter, substrate properties				
2	1-8	Atomic weight	amu	F8.3
	9-16	Bare work function	eV	F8.3
	17-24	Full coverage work function	eV	F8.3
	25-32	Heat of sublimation	eV	F8.3
	33-40	Metallic radius	Å	F8.3
	41-48	Bond strength	—	F8.3
	49-56	Substrate atom density	Å <sup>-2</sup>	F8.3
	57-64	Adsorption site density	Å <sup>-2</sup>	F8.3
	65-72	D <sub>1</sub>	eV	F8.3
	73-80	Blank		F8.3
Parameter, vapor properties				
3	1-8	Atomic weight	amu	F8.3
	9-16	Heat of sublimation	eV	F8.3
	17-24	Metallic radius	Å	F8.3
	25-32	Bond strength	—	F8.3
	33-40	Ionization potential	eV	F8.3
	41-48	Electron-neutral cross section	Å <sup>2</sup>	F8.3
	49-56	Ion-neutral cross section	Å <sup>2</sup>	F8.3
	57-80	Blank		F8.3

Table 1 (contd)

Card	Columns	Parameter	Units	Format
4	1-5	Number of substrate temperatures to be read	—	I5
	6-80	Blank		
5	1-10	Substrate temperature $T_s$	K	F10.5
	11-15	Number of adsorbate temperatures to be read in for the given substrate temperature (NURT)	—	I5
	16-80	Blank		
Parameter, NURT				
6	1-10	Adsorbate temperature $T_R$	K	F10.5
	11-80	Blank		




Fig. 1. Bonding interactions




Fig. 2. Maximum ligancy on the 111-plane of tungsten




Fig. 3. SURFAS subroutine flowchart




Fig. 4. Variation in  $\phi (T_S/T_R, \phi_0)$






Fig. 5. Variation in  $\phi (T_S/T_R, \sigma_s)$




Fig. 6. Variation in  $\phi (T_S/T_R, \sigma_a)$




Fig. 7. Variation in  $\phi$  ( $T_S/T_R$ ,  $D_1$ )




Fig. 8. Rhenium work function

APPENDIX A

PROGRAM LISTING

```

DIMENSION RAT(10),WF(10)
COMMON AG,HG,RG,SG,VIG,VALG,CSEG,CSIG
REAL JO,IO
VALG=1.0
CALL PLOTS
CALL PLOT(0.0,0.0,-3)
READ(5,100) NUCS
DO 10 NUCSN=1,NUCS
READ(5,101) AS,FOS,FCS,HS,RS,SS,SDS,ADS,CS
READ(5,101) AG,HG,RG,SG,VIG,CSEG,CSIG
READ(5,100) NUSB
WRITE(6,120)
WRITE(6,103) AS,FOS,FCS,HS,RS,SS,SDS,ADS,CS
WRITE(6,121)
WRITE(6,103) AG,HG,RG,SG,VIG,CSEG,CSIG
WRITE(6,122)
DO 10 NUSBCN=1,NUSB
READ(5,102) TS,NURT
I=NURT+1
J=I+1
WF(I)=2.0
WF(J)=0.25
RAT(I)=2.0
RAT(J)=0.25
IF(NUSBCN.NE.1) GO TO 3
CALL PLOT(12.0,0.0,-3)
CALL AXIS(0.0,0.0,5HTS/TR,-5,10.0,0.0,RAT(I),RAT(J))
CALL AXIS(0.0,0.0,12HWORK FUNCTION,13,10.0,90.0,WF(I),WF(J))
3 CONTINUE
DO 9 NURTCN=1,NURT
READ(5,102) TR
PG=2.45E+8*EXP(-8910.0/TR)/SQRT(TR)
CALL SURFAS (AS,FOS,FCS,HS,RS,SS,SDS,ADS,CS,TS,PG,WFSO,JO,IO,DS,
1 NOCONV)
RATIO=TS/TR
IF (NOCONV.NE.1) GO TO 4
WRITE (6,107) TS,TR
WF(NURTCN) =2.0
RAT(NURTCN)=RATIO
NOCONV = 0
GO TO 9
4 CONTINUE
RAT(NURTCN)=RATIO
WF(NURTCN)=WFSO
IF(NURTCN.NE.1) GO TO 5

```



```

-----WRITE(6,103) TS,TR,RATIO,WFSO,JO,IO,DS
GO TO 9
5 CONTINUE
-----WRITE(6,106) TR,RATIO,WFSO,JO,IO,DS
9 CONTINUE
-----CALL LINE(RAT,WF,NURT,1,-1,NUSBCN)
10 CONTINUE
-----CALL PLOT(10.0,0.0,999)
100 FORMAT(I5)
101 FORMAT(10F8.3)
102 FORMAT(F10.5,I5)
103 FORMAT(1H0,9F12.3)
104 FORMAT(1H0,18H          GAP SPACING =,F5.1)
120 FORMAT(108H0          AT WT      B W FUN      C W FUN      SUR HEAT      R
1ADIUS      BOND STR      SUB DEN      ADS DEN      D1 ENERGY)
121 FORMAT( 84H0          AT WT      SUB HEAT      RADIUS      BOND STR      IO
1N PCT      E-N XSEC      I-N XSEC)
122 FORMAT( 84H0          SUB TEMP      RES TEMP      TS/TR      WORK FUN
1      JO          IO      FRAC COV)
105 FORMAT(1H0,5F12.3,F12.6,F12.4)
106 FORMAT(13X,4F12.3,F12.6,F12.4)
107 FORMAT(11X,3CHSURFAS IS UNCONVERGED FOR TS =,F8.2,10H AND TR =,F
18.2)
-----END
-FOR,IN SURFAS
-----SUBROUTINE SURFAS(AS,FOS,FOG,HS,RS,SS,SSS,ASS,C,TS,PG,FS,EES,EIS,C
1S,NOCONV)
CSURFAS SURFACE PHYSICS SUBROUTINE
COMMON AG,HG,RG,SG,VIG,VALG,CSEG,CSIG
CC
C EVALUATE ADSORPTION SYSTEM PARAMETERS
CC
SWG = 2.0
SDS = 100.0*SSS
ADS = 100.0*ASS
R = RG + RS
COSB = SQRT(1.0 - 50.0/(SDS*R**2.0))
ALF = RG**3 + 1.65*RS**3
C1 = 0.905*R*ADS*COSB/(1.0+ALF/R**3)
C2 = 9.0E-3*ALF*ADS**1.5
C3 = C
S = 2.0/(SG/SS + SS/SG)
DO = SQRT(HS*HG)*S
ARS = 0.56E+4*PG/SQRT(AG*TS)
CC
C BEGIN SURFACE COVERAGE ITERATION
CC

```

```

-----
NCS = 0
CS = 0.5
DELCS = 0.5
10 CONTINUE
NCS = NCS + 1
IF(NCS.GT.35) GO TO 45
G = 1.0 - 3.0*CS*CS + 2.0*CS*CS*CS
DG = -6.0*CS*(1.0-CS)
CC
C BEGIN FRACTIONAL CHARGE TRANSFER ITERATION
CC
NF = 0
F=0.5
12 CONTINUE
NF = NF + 1
IF(NF.GT.15) GO TO 45
FOF = DO*F/SQRT(1.0-F**2) + C3*F - (FOS-FOG)*G
DFOF = DO/((1.0-F**2)**1.5 + C3)
FN = F - FOF/DFOF
IF(FN.LE.0.0) FN = 0.5*F
IF(FN.GE.1.0) FN = 0.5*(1.0+F)
IF(ABS(FN-F).LE.0.01) GO TO 15
F = FN
GO TO 12
CC
C END FRACTIONAL CHARGE TRANSFER ITERATION
CC
15 FAS = DO*SQRT(1.0-F**2) - 0.5*C3*F**2 + F*(FOS-FOG)*G
DFAS = F*(FOS-FOG)*DG
FS = FOG + (FOS-FOG)*G - F*C1*CS/(1.0+C2*CS**1.5)
FREQ1 = 2.50E-6*SQRT(FAS)*SQRT((AG+4.0*AS)/(2.0*AG*AS))/(R*COSD)
U = 0.5*CS*DFAS/FAS
FREQ = FREQ1*EXP(U)
ENT = EXP(0.5*(CS/(1.0-CS)+SQRT(CS)/(1.0-SQRT(CS))))/(SQRT(1.0-CS)
1*(1.0-SQRT(CS)))
ERS = 1.0E+14*FREQ*SWG*ADS*CS*ENT*EXP(-11600.0*FAS/TS)
IF(ABS((ERS-ARS)/ARS)-0.005)40,20,20
20 IF(ERS-ARS)25,40,30
25 DELCS = DELCS/2.0
CS = CS + DELCS
GO TO 10
30 DELCS = DELCS/2.0
CS = CS - DELCS
GO TO 10
CC
C END SURFACE COVERAGE ITERATION
CC

```

```

C----- COMPUTE ELECTRON AND ION EMISSION CURRENT DENSITIES
CC
40 EFS = .120.0*TS**2*EXP(-11600.0*FS/TS)
   EIS = 2.598E+1*PG*EXP(11600.0*(FS-VIG)/TS)/SQRT(AG*TS/11600.0)
   GO TO 50
45 CONTINUE
   NOCONV=1
50 CONTINUE
   RETURN
   END
-MAP
LIB LIR*PLOTS
-XQT
1
186.2      4.8      1.95      8.07      1.35      2.62      0.101      0.029      0.72
133.0      0.73      2.66      1.0      3.89      400.      570.0
5
2043.      3
486.4
475.1
464.3
1940.      4
485.0
473.2
461.9
451.2
1840.0      5
511.1
497.3
484.2
471.8
460.0
1740.0      5
511.8
497.1
483.3
470.3
457.9
1660.0      7
535.5
518.8
503.0
488.2
474.3
461.1
448.6
-FIN
NIF-

```

## APPENDIX B

### PROGRAM OUTPUT



Reproduced from  
best available copy.

BXBT								
AT WT	B W FUN	C W FUN	SUB HEAT	RADIUS	BOND STR	SUB DEN	ADS DEN	D1 ENERGY
186.203	4.900	1.950	9.070	1.350	2.520	.101	.029	.720
AT WT	SUB HEAT	RADIUS	BOND STR	ION POT	E-N XSEC	I-N XSEC		
133.000	.730	2.550	1.000	3.890	400.000	570.000		
SUB TEMP	RES TEMP	TS/TR	WORK FUN	JO	IO	FRAC COV		
2343.000	486.400	4.200	4.139	.031	2.714989	.1118		
	475.100	4.300	4.260	.016	3.534752	.0920		
	464.300	4.400	4.378	.003	4.503619	.0737		
1940.000	485.000	4.000	3.885	.037	.625182	.1523		
	473.200	4.100	4.017	.017	.882868	.1313		
	461.900	4.200	4.148	.008	1.231198	.1104		
	451.200	4.300	4.279	.003	1.728322	.0898		
1640.000	511.100	3.600	3.360	.257	.058077	.2354		
	497.300	3.700	3.482	.119	.078551	.2153		
	484.200	3.800	3.611	.053	.110640	.1943		
	471.900	3.900	3.752	.022	.157962	.1733		
	460.000	4.000	3.888	.009	.247249	.1519		
1740.000	511.900	3.400	3.108	.355	.009419	.2773		
	497.100	3.500	3.227	.165	.012614	.2573		
	483.300	3.600	3.351	.072	.017518	.2368		
	470.300	3.700	3.476	.031	.024611	.2163		
	457.900	3.800	3.608	.013	.036023	.1948		
1660.000	535.500	3.100	2.756	1.430	.001355	.3386		
	518.900	3.200	2.858	.702	.001542	.3191		
	503.000	3.300	2.981	.298	.002294	.2993		
	488.200	3.400	3.098	.131	.003086	.2791		
	474.300	3.500	3.218	.057	.004245	.2588		
	461.100	3.600	3.343	.024	.006035	.2397		
	448.600	3.700	3.473	.010	.008846	.2168		




Fig. B-1. Work function vs temperature ratio